

BOSS®
PRODUCTS



100 Multi-Seal®

SELF-LEVELING

BUILDING • CONSTRUCTION • CONCRETE

Colors:

825 ml Cartridge

Black - 10022

Grey - 10023

Limestone - 10027

Tan - 10029



- Plastic cartridge
- Long life reliability; cured sealant stays flexible without tearing, cracking, drying out or becoming brittle
- Permanently flexible
- Good UV resistance and color stability
- Paintable with most latex paints*
- Abrasion resistant
- VOC compliant
- Free from solvents and isocyanates

*Test small area for compatibility before painting

THE IDEAL SEALANT/ADHESIVE FOR:

- Vinyl
- Fiberglass
- ABS plastic
- Nylon 6/6
- Polycarbonate
- PVC
- Porcelain tiles
- Glass
- Sealing joints
- Joints between automotive panels
- And more...

Visit Our Website for Other
BOSS® MADE TO WORK Products
www.bossproducts.com

BOSS® 125 Multi-Seal® Roofing, Gutter
Concrete, Construction Sealant

BOSS® 380 Contractors RTV Silicone

BOSS® 363 50 Year Sealant Acrylic Latex

BOSS® 334 Minimal Expanding Straw Foam



Call The **BOSS®** 800-928-BOSS

Soudal Accumetric

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

100 Multi[™]Seal[®]

SELF-LEVELING

BUILDING • CONSTRUCTION • CONCRETE

TYPICAL PROPERTIES**Uncured**

Flow Sag or Slump	Self Leveling
Skin-Over Time	8 min.
Tack Free Time	20 min.
Viscosity, CPS	100,000

Cured – Physical**7 Days at 77°F (25°C) and 50% RH (1/8" thickness)**

Durometer Shore A Hardness	60 points
Specific Gravity	1.55
Tensile Strength	275 psi
Elongation	200%
Modulus	220 psi
Shrinkage	NIL
Service Temperature	-40°F to 200°F
Application Temperature	-35°F to 140°F

Information on this data sheet is subject to change without notice and should not be used for writing specifications.
For additional information on specific applications, contact Soudal Accumetric.

LIMITATIONS

- Do not use for structural glazing
- It is the sole responsibility of the user to test the adhesion to the substrate for suitability

CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

Call The **BOSS[®]** 800-928-BOSS

Soudal Accumetric

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

www.bossproducts.com

