

# BOSS<sup>®</sup> PRODUCTS



# 100 Multi-Seal<sup>®</sup>

## SELF-LEVELING BUILDING • CONSTRUCTION • CONCRETE

### Colors:

825 ml Cartridge

Black - 10022

Grey - 10023

Limestone - 10027

Tan - 10029



- Plastic cartridge
- Long life reliability; cured sealant stays flexible without tearing, cracking, drying out or becoming brittle
- Permanently flexible
- Good UV resistance and color stability
- Paintable with most latex paints\*
- Abrasion resistant
- VOC compliant
- Free from solvents and isocyanates

\*Test small area for compatibility before painting

### THE IDEAL SEALANT/ADHESIVE FOR:

- Concrete expansion joints
- Pool Decks and coping
- Ceramic, masonry, and natural stone
- Patios and sidewalks
- Factories and warehouses

Visit Our Website for Other  
**BOSS<sup>®</sup> MADE TO WORK** Products  
[www.bossproducts.com](http://www.bossproducts.com)

**BOSS<sup>®</sup> 125 Multi-Seal<sup>®</sup> Roofing, Gutter  
Concrete, Construction Sealant**

**BOSS<sup>®</sup> 380 Contractors RTV Silicone**

**BOSS<sup>®</sup> 363 50 Year Sealant Acrylic Latex**

**BOSS<sup>®</sup> 334 Minimal Expanding Straw Foam**



Call The **BOSS<sup>®</sup>** 800-928-BOSS

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

# 100 Multi-Seal<sup>®</sup>

## SELF-LEVELING

### BUILDING • CONSTRUCTION • CONCRETE

#### TYPICAL PROPERTIES

##### Uncured

Flow Sag or Slump ..... Self Leveling  
 Skin-Over Time ..... 8 min.  
 Tack Free Time ..... 20 min.  
 Viscosity, CPS ..... 100,000

##### Cured – Physical

**7 Days at 77°F (25°C) and 50% RH (1/8" thickness)**

Durometer Shore A Hardness ..... 60 points  
 Specific Gravity ..... 1.55  
 Tensile Strength ..... 275 psi  
 Elongation ..... 200%  
 Modulus ..... 220 psi  
 Shrinkage ..... NIL  
 Service Temperature ..... -40°F to 200°F  
 Application Temperature ..... -35°F to 140°F

Information on this data sheet is subject to change without notice and should not be used for writing specifications.  
 For additional information on specific applications, contact Soudal Accumetric.

#### COVERAGE Approximate number of sealable linear feet with BOSS<sup>®</sup> 100 Multi-Seal<sup>®</sup> 29 oz. (825 ml) cartridge.

Depth of Joint	Width of Joint							
	1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
1/8"	279.1	139.6	93	69.8	55.9	46.5	39.9	34.9
1/4"	139.6	69.8	46.4	34.9	27.9	23.3	19.9	17.4
3/8"	93	46.4	31	23.3	18.6	15.5	13.3	11.6
1/2"	69.8	34.9	23.3	17.4	14	11.6	10	8.7
5/8"	55.8	27.9	18.6	14	11.2	9.3	8	7
3/4"	46.5	23.3	15.5	11.6	9.3	7.7	6.6	5.8
7/8"	39.9	19.9	13.3	10	8	6.6	5.7	5
1"	34.9	17.4	11.6	8.7	7	5.8	5	4.4

#### LIMITATIONS

• Do not use for structural glazing • It is the sole responsibility of the user to test the adhesion to the substrate for suitability

#### CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

Call The **BOSS<sup>®</sup>** 800-928-BOSS  
 350 Ring Road • Elizabethtown • KY 42701  
 (270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412  
[www.bossproducts.com](http://www.bossproducts.com)

