

# BOSS<sup>®</sup> PRODUCTS



# 140 Multi-Seal<sup>®</sup>

## NEXT GENERATION SEALANT FOR MARINE • BOAT • DECKING

### Colors:

White - 14001  
Black - 14002



- VOC Compliant in all 50 states
- Ease of use, one-part sealant, no mixing required
- Good weatherability - virtually unaffected by sunlight, rain, snow, ozone and temperature extremes
- Good UV resistance and color stability
- Long life reliability; cured sealant stays flexible without tearing, cracking, drying out or becoming brittle
- Non-yellowing and non-staining
- Sandable and paintable with most latex base paints\*
- Free from solvents and isocyanates
- Non-corrosive and non-flammable
- Primerless adhesion to damp and non-porous surfaces
- No in-gassing
- Temperature resistant up to 200°F
- Permanently flexible
- Can be used under water when a permanent gasket seal is required between two substrates
- Mildew Resistant

\*Test small area for compatibility before painting

### 3000 HOURS IN WEATHEROMETER

#### “The Competition”



Before

After

#### BOSS 140



Before

After

Call The **BOSS**<sup>®</sup> 800-928-BOSS

**Soudal Accumetric**

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

# 140 Multi-Seal<sup>®</sup>

## NEXT GENERATION SEALANT FOR MARINE • BOAT • DECKING

### TYPICAL PROPERTIES

#### Uncured

Flow Sag or Slump .....	NIL
Tack Free Time. ....	35 min.
Extrusion Rate .....	240 g/min.

#### Cured – Physical

##### 7 Days at 77°F (25°C) and 50% RH (1/8" thickness)

Durometer Shore A Hardness .....	50 points
Specific Gravity .....	1.60
Tensile Strength.....	335 psi
Elongation .....	220%
Shrinkage .....	NIL
Service Temperature.....	-40°F to 200°F
Application Temperature .....	-35°F to 140°F

Information on this data sheet is subject to change without notice and should not be used for writing specifications.  
For additional information on specific applications, contact Soudal Accumetric.

### LIMITATIONS

- Do not use for structural glazing
- It is the sole responsibility of the user to test the adhesion to the substrate for suitability

### CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE, AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

Call The **BOSS<sup>®</sup>** 800-928-BOSS  
Soudal Accumetric

350 Ring Road • Elizabethtown • KY 42701  
(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412  
[www.bossproducts.com](http://www.bossproducts.com)

