

# 150 Multi-Seal<sup>®</sup>

## INDUSTRIAL • COLD STORAGE REFRIGERATION • CONSTRUCTION

- Plastic cartridge
- Non-Yellowing
- Safe for use around food processing areas
- Long-lasting, flexible adhesive
- Paintable in under an hour\*
- Low Temperature flexibility
- Qualifies for LEED Credits
- VOC compliant
- Solvent & isocyanate free formulation
- Bonds to Kynar 500
- NSF Compliant

\*Test small area for compatability before painting

### THE IDEAL SEALANT/ADHESIVE FOR:

- Stainless and galvanized steel
- Coolers
- Freezers
- Metal
- Most common building materials

Visit Our Website for Other  
**BOSS<sup>®</sup> MADE TO WORK** Products  
[www.bossproducts.com](http://www.bossproducts.com)

**BOSS<sup>®</sup> 125 Multi-Seal<sup>®</sup> Roofing, Gutter,  
Concrete, Construction Sealant**

**BOSS<sup>®</sup> 370 HVAC/R RTV Silicone Adhesive**

**BOSS<sup>®</sup> 376 Hi-Temp Red RTV Silicone**

**BOSS<sup>®</sup> 893 Dual Sided - Smooth/Abrasive Wipes**

### Colors:

### Cartridge

Polar White - 15001

Pitch Black - 15002

Stainless Steel - 15003



Call The **BOSS<sup>®</sup>** 800-928-BOSS

**Soudal Accumetric**

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412



# 150 Multi-Seal<sup>®</sup>

## INDUSTRIAL • COLD STORAGE REFRIGERATION • CONSTRUCTION

### TYPICAL PROPERTIES

#### Uncured

Flow Sag or Slump ..... NIL  
Tack Free Time ..... 23 min.  
Extrusion Rate ..... 380 g/min.

#### Cured – Physical

##### 7 Days at 77°F (25°C) and 50% RH (1/8" thickness)

Durometer Shore A Hardness ..... 40 points  
Specific Gravity ..... 1.55  
Tensile Strength ..... 200 psi  
Elongation ..... 350%  
Modulus ..... 125 psi  
Shrinkage ..... NIL  
Service Temperature ..... -40°F to 200°F  
Application Temperature ..... -35°F to 140°F

Information on this data sheet is subject to change without notice and should not be used for writing specifications.  
For additional information on specific applications, contact Soudal Accumetric.

### LIMITATIONS

- Do not use for structural glazing
- It is the sole responsibility of the user to test the adhesion to the substrate for suitability

### CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

Call The **BOSS<sup>®</sup>** 800-928-BOSS  
Soudal Accumetric

350 Ring Road • Elizabethtown • KY 42701  
(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412  
[www.bossproducts.com](http://www.bossproducts.com)

