

BOSS® PRODUCTS



338 Flexible Foam

PROFESSIONAL GUN GRADE

Part Number:
33824



- Very high elastic recovery
- Copes with extreme mechanical movement without cracking
- Excellent adhesion on most substrates (except Teflon, PE and PP)
- High thermal and acoustical insulation performance
- Very good filling capacities
- Excellent stability (no shrink or post expansion)
- Very precise application due to the foam applicator gun system
- Low expansion
- Good compressibility

THE IDEAL SEALANT/ADHESIVE FOR:

- Ideal for restricting air, sound, dirt, and water vapor
- Sealing around door and window frames
- Sealing around pipes, vents and electrical outlets
- Filling joints and insulating wall panels
- Filling gaps under corrugated sheets or roof tiles

Visit Our Website for Other
BOSS® MADE TO WORK Products
www.bossproducts.com



Foam Gun-Plastic Tip Compact
144150

Call The **BOSS®** 800-928-BOSS
350 Ring Road • Elizabethtown • KY 42701
(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

338 Flexible Foam

PROFESSIONAL GUN GRADE

TYPICAL PROPERTIES

| | |
|--|---|
| Skin-over Time (1" bead)..... | 6 minutes (68°F & 65% R.H.) |
| Tack Free (1" bead)..... | Dustfree after 20-25 min. at 68°F |
| Cure Time (1" bead) | 1 hour |
| Tensile Strength | 2.2 psi |
| Shear Strength | 3.6 psi |
| Yield/24 Oz. Can | 6.6 gallons of cured foam |
| Theoretical Yield - 24 oz. 1/4" bead | 4005 ft. |
| Elastic Recovery (ISO 1856)..... | Until 92% (75% compressed) |
| Acoustic Rating (EN ISO 717-1) | $R_{ST,W} (c; c_{tr}) = 60\text{dB} (-1; -4)$ |
| Service Temperature..... | -40°F to 194°F |
| Application Temperature | -13°F to 120°F |

*Information on this data sheet is subject to change without notice and should not be used for writing specifications.
For additional information on specific applications, contact Soudal.

LIMITATIONS

- Ground shipments only. Cannot ship by air.
- Reactive VOC 149 g/l (16% wt)
- It is the sole responsibility of the user to test the adhesion to the substrate for suitability

DANGER!

EXTREMELY FLAMMABLE. CONTENTS UNDER PRESSURE.

Call The **BOSS[®]** 800-928-BOSS

Soudal Accumetric

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

www.bossproducts.com

