

BOSS[®] 357 Painters Latex Caulk

TYPICAL PROPERTIES

Colors	White
% Non-Volatile, by weight.....	83.5%
% Volume Shrinkage: ASTM C-733-87.....	28%
Weight, approximate	14.3 lb./gal. 1.7135 kg/L
pH.....	7.0 - 8.7
Slump	<.2”
Tack-Free Time: ASTM D-2377-84.....	25 minutes
Elongation	300%
Volatile Organic Content (VOC minus water).....	8.6 grams/liter
Service Temperature.....	-20°F to 185°F
Application Temperature	40°F to 110°F

*Information on this data sheet is subject to change without notice and should not be used for writing specifications.
For additional information on specific applications contact Soudal.



DESCRIPTION

BOSS[®] 357 Painters Latex Caulk was designed for both interior and exterior use. **BOSS[®] 357** cures to form a flexible, non-yellowing seal without staining or bleeding and is compatible with a wide variety of substrates.

BOSS[®] 357 Painters Latex Caulk was developed for use around windows, door frames, baseboards or any joint or gap where a weather-tight seal is required. **BOSS[®] 357** adheres well to wood, masonry, brick and plaster.

USES

- Sealing around window and door frames
- Sealing around baseboards
- Sealing around trim
- Sealing anywhere a weathertight seal is desired
- Sealing corner joints

HOW TO USE

BOSS® 357 Painters Latex Caulk should only be used where slight joint movement is anticipated. In extremely deep joints, use foam joint filler.

Tooling is recommended and, if possible, should be completed in one continuous stroke.

Tool joints within ten minutes of application. If masking tape has been used to obtain a cleaner joint it should be removed before the tack-free skin forms.

PAINTABILITY

A minimum of 2 hours dry time is required before painting with latex or oil base paint. Allow extra dry time during periods of high humidity and/or cool temperatures.

CLEAN UP

Excess caulk should be cleaned off tools and nonporous surfaces while it is in the uncured state using a wet cloth. Cured compounds should be cut away.

COLORS

BOSS® 357 Painters Latex Caulk is available in white.

PACKAGING

BOSS® 357 Painters Latex Caulk is available in standard caulking cartridges.

SHIPPING LIMITATIONS

None.

Nonreactive VOC 9 g/l (<1.5% wt)

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **BOSS® 357** Painters Latex Caulk has a shelf life of 12 months from date of shipment. In countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the nozzle tip pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building. **KEEP FROM FREEZING.**

CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Soudal's control, we can accept no liability for the results obtained. Soudal's sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Soudal will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

MADE IN U.S.A.

BOSS® PRODUCTS

Soudal

350 Ring Road / Elizabethtown, KY 42701 USA
800-928-BOSS(2677)

TEL (270)769-3385 / FAX (270)765-2412

Outside U.S.

TEL +1(270)769-3385 / FAX +1(270)765-2412

www.bossproducts.com