

### CLEAR SILICONE ADHESIVE/SEALANT PART NOS. 143372, 143376, 143400

#### TYPICAL PROPERTIES

##### Uncured

Physical Form..... Non-Slumping Paste  
Color ..... Clear  
Specific Gravity @ 77°F (25°C)..... 1.02  
Extrusion Rate (1/8" orifice, 90 psi), gms/min..... 400  
Flow Rate (sag or slump  
on 1/8" X 4" bead), in. .... NIL  
Tack-Free Time @ 77°F (25°C) and  
50% RH, min ..... 10-20  
Cure Time @ 77°F (25°C) and 50% RH  
(1/8" thick), hrs..... 24

##### Cured – Physical

ASTM D 676 Durometer Hardness,  
Shore A, points ..... 24  
ASTM D 412 Tensile Strength, psi (MPa) ..... 350  
ASTM D 412 Elongation, % ..... 500  
ASTM D 746 Brittle Point, degrees ..-100°F (-73°C)  
ASTM D 2137A Volume Coefficient of Thermal  
Expansion, 32°F to 212°F.....  $9.3 \times 10^{-4}$   
Thermal Conductivity, cal/(cm  
(degree C), (sec) .....  $0.45 \times 10^{-3}$   
BTU per (ft) (degrees F) (hr.) ..... 0.11  
Service Temperature..... -40°F to 400°F  
Application Temperature ..... -35°F to 140°



#### DESCRIPTION

*Dynatex® Clear Silicone Adhesive/Sealant* is a paste-like, one-component material, which cures to a tough, rubbery solid upon exposure to moisture in the air. Provides transparent, watertight silicone rubber seal for a wide range of applications. Seals, insulates and bonds. Works well on marine, recreational and industrial applications.

#### FEATURES

- Bonds and seals
- Waterproof and weatherproof seal
- Insulates thermally and electrically
- Permanently flexible

#### TYPICAL APPLICATIONS

- Windshields
- Sunroofs
- Tail-lights
- Interior panels
- Firewalls
- Dashboards and more...

#### BONDS AND SEALS:

- Auto and appliance trim, including metal, fabric and fabric backed plastics
- Glass, vinyl, wood and rubber
- Trailers, truck cabs
- Frayed wires

#### Packaging

Colors: Clear

Size: 3 Oz Tube, 8 Oz Auto can, 300ml Cartridge

## LIMITATIONS

*Dynatex® Clear Silicone Adhesive/Sealant* will corrode and will not adhere to copper, brass (and other copper-containing alloys), magnesium, zinc, galvanized metals (and other zinc-containing alloys).

*Dynatex® Clear Silicone Adhesive/Sealant* has good resistance to weathering, vibration, moisture, ozone and extreme temperatures. It may be applied in sub-zero weather without loss of extrusion or physical property characteristics and is effective to -35°C (-30°F). Fully cured *Dynatex® Clear Silicone Adhesive/Sealant* can be used for temperatures up to 450°F (232°C).

## CURE TIME

Cure time is affected by relative humidity, degree of confinement and cross-sectional thickness of the sealant. Sections up to 1/8-inch thick become rubbery solids in about 24 hours at room temperature at 20-percent relative humidity. Less moisture content reduces cure time slightly. In 24 hours, sections up to 1/8-inch thick cure to a rubber with a Shore A Durometer Hardness of about 20 points. After 3 days at room temperature, this durometer hardness levels off to about 24 points.

In applications where *Dynatex® Clear Silicone Adhesive/Sealant* may be partially or totally confined during cure, the time required for proper cure is generally lengthened by the degree of confinement. It is possible that with absolute confinement cure will not be completed. The result is the softening of the sealant at elevated temperatures. Metal-to-metal bonds should not overlap more than one inch. Every application involving confinement during cure should be thoroughly tested before commercialization.

Curing time increases with the thickness of the sealant. A 1/2-inch cross section, for example, may require 3 or 4 days for complete solidification. However, the cure will have penetrated the outer 1/8-inch in about 24 hours.

An odor caused by the liberation of acetic acid is given off during cure. This odor disappears as the cure progresses and is not detectable after cure is complete.

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), *Dynatex® Clear Silicone Adhesive/Sealant* has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

## USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

**Non-warranty:** Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted. Suggestions of uses should not be taken as inducements to infringe any patents.

**Dynatex®** a division of **SOUDAL**

350 Ring Road  
Elizabethtown, KY 42701  
Email: sales@dynatex.net

Toll Free: (800) 999-2937  
Ph: (270) 769-5557  
Fax (270) 769-6418

Website: www.dynatex.net