





# TECHNICAL DATA SHEET

# PIPE SEALANT WITH PTFE **PART NO. 143466**

## TYPICAL PROPERTIES OF UNCURED **SEALANT**

Chemical Type	Methacrylate Esters
Appearance	White opaque paste
Viscosity	400,000 cps (mPas)
Specific Gravity	1.15
Flash Point	>95°C
Solids	100%
Shelf Life @ 21°C	12 months

#### **DESCRIPTION**

**Dynatex**<sup>®</sup> Pipe Sealant w/PTFE provides immediate low pressure sealing performance on tapered pipe threads. The product is designed to cure when in contact with metals, and without air by anaerobic reaction up to the burst rating of the pipe itself. The product cures to a solid plastic, completely sealing against hydraulic fluids, air, most gasses, and most chemicals. It is an excellent replacement for pipe dopes and pipe tapes.

### **FEATURES:**

## \*Certified to ANSI/NSF 61 Section 6 – Drinking Water System Components

- Seals instantly to moderate pressures
- Fully cures at room temperature to burst pressure of most piping systems
- Will not crack or shrink because of solvent evaporation
- Superior resistance to a wide range of chemicals
- Controlled strength for easy disassembly
- High temperature resistance
- Locks pipe and fittings against vibration loosening, tampering, and variable temperature effects

### **TYPICAL APPLICATIONS:**

- Automotive
- Appliance
- Construction
- Fire Protection
- Plumbing
- Utilities
- Petroleum refining
- Chemical processing



#### **GENERAL INSTRUCTIONS**

Apply sealant to the leading threads of the male fittings except for the first thread, which should be left free of sealant. Force sealant into the threads to thoroughly fill the voids. Best results will be obtained on fittings that are free of grease and oil. Assemble and wrench-tighten fittings until proper alignment is obtained. Properly tightened fittings will seal instantly to moderate pressures. For maximum pressure and solvent resistance allow sealant to fully cure (24 hour or more depending on temperature).

## **TYPICAL CURED PERFORMANCE (Straight** Threads):

The performance and locking strength on 3/8 inch (9.5mm) Zinc plated nuts and bolts is:

> Fixture time: <45 minutes Breakaway Torque: 45 in-lb (5.0 Nm) Prevailing Torque: 25 in-lb (2.8 Nm)

# **Packaging**

Colors: White

Size: 50ml Tube Carded

### TYPICAL CURED PERFORMANCE (Tapered Threads):

Immediate sealing: Instant sealing is a function of the on-torque assembly, type of fitting, grade of fitting, part and ambient temperature among other items. The typical immediate or instant low pressure sealing capability of *Dynatex® Pipe Sealant w/PTFE* is 1000psi (6.9Mpa) when hand assembled, and 3000psi (20.7Mpa) when a 10in-lb (1.1 Nm) ontorque is applied.

Full cure sealing: Maximum sealing capabilities occur after full cure. Typically, this is up to the burst rating of the pipe or fitting itself, which can be in excess of 40,000psi (275Mpa). The time it takes to achieve full cure depends on substrate and the temperature. Full cure may take in excess of 24 hours at low ambient temperature and with inactive metals. Some typical examples of substrate activity are:

<b>Super Active</b>		Inactive	Passive
Very Fast Cure	Fast Cure	Slow Cure	Primer
			necessary
Brass, Copper,	Iron,	Stainless Steel,	Ceramics,
Magnesium	Steel,	Titanium, Zinc,	Glass, Plastics,
	Nickel,		Painted finishes
	Aluminum	Aluminum	

### **CHEMICAL/SOLVENT RESISTANCE**

Solvent	Temp	% Of initial Strength after 30 days immersion
Gasoline	190°F (88°C)	100
Motor Oil	190°F (88°C)	100
Brake Fluid	190°F (88°C)	98
Distilled Water	190°F (88°C)	100
Isopropyl Alcohol	190°F (88°C)	100
Perchloroethane	190°F (88°C)	100
Diesel Fuel	190°F (88°C)	100
Transmission Fluid	190°F (88°C)	100

### COMPATIBILITY

Uncured **Dynatex**® Pipe Sealant w/PTFE will soften and can damage thermoplastics including ABS, polycarbonate, and vinyl, Methacrylates etc. will also soften varnish and lacquer finished. It is compatible with all metals, glass, ceramics and thermoset plastics such as phenolic and polyester.

**Dynatex**<sup>®</sup> Pipe Sealant w/PTFE is not recommended for pure oxygen or oxygen enriched systems and should not be used as a sealant for chlorine gas, liquid, or other strong oxidizing systems.

### **STORAGE AND SHELF LIFE**

When stored in the original unopened containers at or below 90°F (32°C), *Dynatex® Pipe Sealant w/PTFE* has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

#### **USERS PLEASE READ**

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.





350 Ring Road Elizabethtown, KY 42701 Email: sales@dynatex.net

Toll Free: (800) 999-2937 Ph: (270) 769-5557 Fax (270) 769-6418 Website: www.dvnatex.net

143466/07-20 MADE IN U.S.A.