

GTX HS 2500 TRAILER SEALANT/ ADHESIVE PART NOS. 145765, 145764

TYPICAL PROPERTIES

Uncured

Appearance	Smooth
Spec Gravity	1.6
Sag/Slump	NIL
Extrusion Rate	250 g/min.
Tack Free Time @ 75°F (24°C) And 50% RH	20min.

Cured – Physical

**7 Days @ 77°F (25°C) and 50% RH
(1/8" thickness)**

Durometer Shore A Hardness	48 points
Tensile Strength	420 psi
Elongation	480%
Modulus (psi)	250 psi
Solid	98%
Service Temperature	-40°F to 200°F
Application Temperature	-35°F to 140°F



DESCRIPTION

Dynatex® GTX HS 2500 Trailer Sealant/Adhesive is a one-component, high performance adhesive/sealant formulated with USP™ Technology. It provides excellent durability, maximum adhesive strength and is VOC compliant in all 50 states. It is designed to resist all on-the-road flexing and vibration. It is fast curing and provides permanent elastic adhesion to most surfaces with quick grab and excellent durability.

FEATURES

- VOC Compliant
- Trailer Sealant/Adhesive
- Non-Streaking or Staining
- Can be applied and tooled in most weather conditions
- Paintable*
- No shrinking
- Flexible

TYPICAL APPLICATIONS

Popular applications include:

- Tractor trailers
- RV's
- Buses
- Van conversions
- Shipping containers and many other adhesive /sealant applications

MEETS

- ASTM C920, Type S, Grade NS, Class 35, Use T, NT, M, A, G & O.
- Federal Specification TT-S-0230C, Type II, Class A

Packaging

Colors: White, Grey
Size: 300ml Cartridge

*Always test small area for compatibility before applying.

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **Dynatex® GTX HS 2500 Trailer Sealant** has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the nozzle tip pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

REMARKS

- Do not use for structural glazing.
- Not recommended for use on PE, PP or PTFE (Teflon) due to poor adhesion to these substrates
- Not recommended for applications below the water line, continuous immersion or for sealing/bonding windshields
- Poor resistance to solvents, concentrated acids and chlorinated hydrocarbons

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

Dynatex® a division of **SOUDAL**

350 Ring Road
Elizabethtown, KY 42701
Email: sales@dynatex.net
Website: www.dynatex.net

Toll Free: (800) 999-2937
Ph: (270) 769-5557
Fax (270) 769-6418