

# Soudafoam MAXTWO HFO E84

**SODAL**

- FIRE CLASSIFICATION ASTM E84/UL723 FSI/SDI <25/<450; full coverage/2" thickness
- High R-value that reduces heating and cooling costs
- No VOCs, non-flammable, <1 GWP, and ODP of 0
- Great for acoustic insulation
- Cures in minutes
- No shrinkage or expansion after curing
- Great adhesion to a variety of surfaces
- 200 boardfoot and 600 boardfoot sizes for different job sizes
- Disposable canisters that require no external power source



**Basement insulation**  
**Residential wall insulation**  
**Cold storage insulation**  
**Pool and spa insulation**

This information and all further technical advice are based on SODAL present knowledge and experience. However, SODAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. SODAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SODAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SODAL reserves the right to make any changes according to technological progress or further developments.

# Soudafoam MAXTWO HFO E84

# SOUDAL

Properties	Value	Unit	Method
Nominal density	1.76	lb/ft <sup>3</sup>	ASTM D1622
Compressive strength	21.2	psi	ASTM D1621
Tensile Strength	43.8	psi	ASTM D1623
Thermal resistance per inch (R-value)	TBD	ft <sup>2</sup> ·h·°F/Btu	ASTM C518
Flame spread/smoke developed* @ 2" thick, full coverage	20/350		ASTM E84/UL723
Air leakage rate at 75 Pa (1" thick)	0.02	L/s/m <sup>2</sup>	ASTM E283
<b>Dimensional stability</b>			ASTM D2126
-40°C (-40°F)	-0.2	%	
70°C/97% RH (158°F/97% RH)	6.6	%	
37.8°C/97% RH (100°F/97% RH)	3.5	%	
Water vapor transmission (2" thick)	1.869	perms	ASTM E96
Gel time	30	s	
Closed Cell Content	>90	%	

Mentioned values are typical for production samples, but are no sales specifications.

\* Note: fire classifications are not intended to reflect hazards presented by this or any other material under actual fire conditions.

### Limitations:

- Listed yield are optimum, and will vary slightly based on application technique and weather conditions when spraying occurs and during the curing time of sprayed product.
- User should review the technical data sheet and product and application guide prior to using the product.
- High temperatures can affect quality and stability of the components, and can lead to creating a sub-optimal foam.

### CAUTION:

Both cylinders are under pressure. Do not puncture the cylinders, do not dispose before emptying. Avoid prolonged storage in direct sunlight or near heat sources. Do not breathe vapors or spray. Use only in a well-ventilated area. Use proper protective clothing (e.g. impermeable coveralls, no skin should be exposed) and chemical resistant gloves. It is recommended to wear respiratory protection, according to OSHA requirements, while operating the Soudafoam MAXTWO HFO systems (e.g. half face mask respirator with appropriate filter) in combination with safety goggles. Check SDS for further information on personal protection and protection of the environment.

PLEASE REFER TO TECHNICAL DATA SHEET FOR COMPLETE INFORMATION ABOUT THE PRODUCT

